

# RANA MARINE AL 7001P

## Product information

- 1- As a red oxide modified alkyd primer
- 2-Resists corrosion.
- 3- A high quality, modified alkyd primer
- 4- for use on boot top, topsides, decks and superstructures

## Physical data

Colour:	Red- brown
Finish:	Flat
Flash point:	24°C
Volume solids:	55 ±2%
D.f.t:	50-75 microns
Specific gravity:	1.40 ± 0.05gr/cm <sup>3</sup>
Theoretical coverage:	11 m <sup>2</sup> /lit (at 50 µ d.f.t)
Drying time at 25°C:	
touch dry:	1hr
dry to handle:	4hrs
full cure:	4days
Component:	1
Application methods:	Conventional spray or brush or airless spray or roller
Recoat intervals*:	10°C            25°C            40°C
(mild condition) : Min:	30 hrs            12 hrs            6 hrs
Max:	748 hrs            24 hrs            12 hrs
Recommended thinner:	RANATHINN 70
Recommended cleaner:	RANA CLEAN 70
Shelf life:	12 months when stored indoors in unopened Original containers at 5 to 40°C (cool and dry place).
Curing mechanism:	By solvent release and chemical reaction with O <sub>2</sub>
Substrate:	Steel

\*: For recoating the surface should be free of dust ,grease and contamination .

## Typical uses

As a primer on interior and exterior steel in mildly to moderately corrosive environment.

# RANA MARINE AL 7001P

## Application information

This RANA CHEM's product is a red iron oxide alkyd primer for above water service.

To obtain the maximum performance for which this product is formulated, strict adherence to all application, instructions, precautions, conditions and limitations is necessary.

## Application equipment

The following equipment is listed as a guide and suitable equipment from other manufactures may be used.

Adjustments of pressure and change of tip size may be needed to obtain the proper spray characteristics.

1-Airless spray: standard airless spray equipment having A 28:1 or higher pump ratio and a fluid tip with a 0.33 to 0.381 mm orifice.

2-Conventional spray: industrial equipment with suitable aircap having a fluid tip with A 1.6-1.8 mm orifice .

3 -Mixer: mixer must be powered by an air motor or an explosion Proof electric motor.

4-Brush or roller.

## Caution

1-Handle with care.

2-Harmful or fatal if swallowed; immediately seek medical assistance.

3-Avoid inhalation of possible solvent vapours or paint mist, as well as paint contact with skin and eyes.

4-Apply only in well ventilated areas and ensure that adequate forced ventilation exists when paint applies is

in confined spaces or when the air is stagnant.

5-Use fresh air masks and explosion proof equipment.

# RANA MARINE AL 7001P

6-Take precautionary measures against static discharges.

## Application procedure

1-Flush equipment with recommended cleaner before use.

2-Stir paint for 5 minutes.

3-For spray, thin only as needed for workability.

4-Apply a wet coat in even, parallel passes. overlap each pass 50% to avoid bare areas, pinholes or holidays.

5-Small damaged or bare areas and random pinholes or holidays can be touched up by brush.

6-Clean all equipment with recommended cleaner immediately after as or at least at the end of each working day or shift.

## Environmental condition

Environmental temperature must be 10-40°C.

Surface temperature must be at least 3°C above dew point to prevent condensation. At freezing temperature surface must be free of ice and relative humidity below 80 %.

## Surface preparation

The surface must be clean and dry . All dirt , grease , millscale and any other foreign material should be removed. sand blasting to standard of Sa 2.5 – Sa3 , sis 05 5900 , iso 8501-1.